

PRODUCT DATA

NON-SKID 200 & 300 ADDITIVES

DESCRIPTION

RUST-OLEUM® Non-Skid 200 & 300 Additives granulates are based on thermally split flint stones.

RECOMMENDED USES

RUST-OLEUM® Non-Skid 200 & 300 Additives are intended to be added to floor coatings to produce a non-skid surface.

RUST-OLEUM Non-Skid 200 & 300 Additives can be used in combination with the following RUST-OLEUM Floor coatings: Flexible Epoxy Flooring System B95 (NS 300 only); Solvent-free High-Build Epoxy System 5500; High-Performance Epoxy System 9100 and Rust-O-Thane® Polyurethane Topcoats 9600 (NS200 only)

RUST-OLEUM Non-Skid 200 & 300 Additives can be mixed with the required RUST-OLEUM coating system or can be sprinkled into the freshly applied coating manually or with special low pressure spraying equipment.

RUST-OLEUM Non-Skid 200 & 300 Additives are intended for Non-Skid industrial flooring and should be topcoated with the required RUST-OLEUM System if sprinkled.

TECHNICAL DATA

Finish:	Produces a rough, non-skid surface
Colour:	White
Particle size :	Anti-Slip 200: 0.2 - 0.5 mm Anti-Slip 300: 0.5 - 1.0 mm
Density:	Anti-Slip 200: 2.26 kg/l Anti-Slip 300: 2.28 kg/l
Solids content:	100% by volume/weight
Recommended consumption:	Sparingly: 20 m ² /kg (= 200 g/l if mixed in) Dense: 10 m ² /kg (= 400 g/l if mixed in)
VOC-content:	0 g/l

Coverage

Theoretical: 50 g/m² sparingly (see Recommended consumption)

Practical: Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

DIRECTION FOR USE

Sprinkling: sprinkle the granulates onto the freshly applied, wet RUST-OLEUM coating, manually with a "sprinkler-box" for small areas, or with special low-pressure spraying equipment with a nozzle opening of at least 18 mm ; air pressure between 1 - 3 bars.

Mixing: mix the granulates into the wet coating material and apply the coating with a roller or a brush (not by spraying), stir regularly to avoid settling of the granulates.

APPLICATION CONDITIONS

For optimum results, follow the application conditions with the applied RUST-OLEUM Floor Coating.

REMARKS

For coating systems with a dry film thickness less than 300 µm it is recommended to use Non-Skid 200.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk