

PRODUCT DATA

HARD HAT® AEROSOLS TOPCOAT 2500

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk

DESCRIPTION

RUST-OLEUM® Hard Hat Aerosols Transparent Topcoat 2500 is a non-yellowing coating, based on fast drying acrylic resin.

RECOMMENDED USES

RUST-OLEUM Transparent Topcoat 2500 should be applied over RUST-OLEUM Hard Hat Fluorescent Topcoats 2200 or Metallic Topcoats 2100 or can be used to restore the gloss of faded old coatings.

RUST-OLEUM Transparent Topcoat 2500 can be applied direct on several metals like: aluminium, brass, bronze, chrome and copper.

RUST-OLEUM Transparent Topcoat 2500 is intended for small maintenance jobs or for touch-up.

RUST-OLEUM Transparent Topcoat 2500 should be used in light industrial exposures, normal humidity and interior applications.

TECHNICAL DATA

Appearance:	High-gloss
Colour:	Transparent
Propellant:	Dimethyl ether
Recommended film thickness:	15 µm dry, equals 60 µm wet
VOC-content:	651 g/l

Drying times	20°C/50% r.v.
To touch:	15 minutes
To handle:	30 minutes
To recoat:	After 1 hour
Full hardness	3 days

Heat resistance:	100°C (dry heat)
------------------	------------------

Coverage

Theoretical: 3.5 m² per spray can at 15 µm dry

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dirt, grease, oil and all other surface contaminants by appropriate means. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

PRODUCT DATA

HARD HAT® AEROSOLS TOPCOAT 2500

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk