

PRODUCT DATA

COMBIPRIMER TACK COAT 3302

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk

DESCRIPTION

RUST-OLEUM® CombiPrimer Tack Coat 3302 is an adhesion coat based on a solvent containing acrylic.

RECOMMENDED USES

RUST-OLEUM CombiPrimer Tack Coat 3302 should be used on on galvanised steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces followed by RUST-OLEUM CombiColor Metal Coating System. CombiPrimer Tack Coat 3302 is primarily intended for brush application.

TECHNICAL DATA

Appearance: Tacky
Colour: Clear/Blue
Density: 0.87 kg/ltr.
Solids Content: 7% by volume
Viscosity: 16-24 sec. Ford cup 4 at 20°C
Recommended film thickness: Not applicable

VOC-content: 741 g/l max.
Ready-to-use mixture: 741 g/l max.
Category: A/h
EU Limit values: 750 g/l (2007) / 750 g/l (2010)

Drying times 20°C/50% r.h.
To touch: Remains tacky
To handle: Remains tacky
To recoat: After ½ hours but within 24 hours
Heat resistance: 100°C (dry heat)

Coverage Theoretical: 35 m²/l
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove previous coatings completely. Remove salts, 'white rust', etc., by washing with RUST-OLEUM Surfa-Etch 108 Etching Solution. The surface must be clean and dry during application.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: Use natural bristles, longhair brushes.
Cleanup: Use RUST-OLEUM Thinner 160.

APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

REMARKS

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

PRODUCT DATA

COMBIPRIMER TACK COAT 3302

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk