

PRODUCT DATA RUST-OLEUM® Waterproof 3486KIT.1/3486.5

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk

DESCRIPTION

Rust-Oleum® Waterproof is an instant leak repair coating based on solvent soluble high polymers (acrylic and alkyd binders) reinforced with fibres.

MAIN PROPERTIES

A ready to use waterproofing repair compound for instant leak repairs in any weather condition - Ideal for repairs to roofs, gutters, drain pipes, ridge-pieces, sky lights, cornices, chimney stacks, pipes, etc. - Seals leaks instantly, even on damp or wet surfaces - Forms a durable elastic coating (1300%) that withstands temperature changes and UV-light - Bridges cracks up to 2 mm (larger cracks can be treated with a special reinforcement fleece) - Adheres to: roofing, felt, slate, corrugated, bitumen, asphalt, hard PVC, polyester, zinc, brickwork, aluminium, glass, tiles and many other substrates - Available in 5 litre packaging or in a handy 1 litre emergency repair set.

RECOMMENDED USES

Waterproof finish of roofs, non-walkable terraces, gutters, ridge-pieces, chimney stacks, pipes, etc.

TECHNICAL DATA

| | |
|-----------------------------|--|
| Appearance: | Fibre structure (gloss 60°: ± 45%) |
| Colour: | Dark grey |
| Density: | 1,01 - 1,04 g/cm ³ |
| Solids Content: | In volume: 41 - 43% |
| | In weight: 49 - 53% |
| Recommended film thickness: | Wet film: 1000 micron (cons.: 1 l/m ²) |
| | Dry film: 430 micron (cons.: 1 l/m ²) |
| VOC-content: | Max. 500 g/l |
| Flashpoint: | 40°C. Flammable |

Drying times 20°C/50% r.h.
To touch: 4 hours
To recoat: 3 - 14 days with the same product.
6 weeks with a paint (see remarks).

Coverage

Theoretical: ± 1 - 2,5 l/m²
Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove any standing water, algae, lichens and loose chippings thoroughly.
Clean the spots to be repaired with a hard broom and wash with a wet sponge.
After cleaning, 3486 can be applied directly on the substrate. Minimum wet film thickness 1 mm. In case of repeatedly repaired spots, important or active cracks, apply 3486 crosswise over the cracks or fissures.

DIRECTION FOR USE

To ensure homogeneity the product should be thoroughly stirred prior to use

PRODUCT DATA RUST-OLEUM® Waterproof 3486KIT.1/3486.5

APPLICATION & THINNING

| | |
|---------------------|--|
| Brush: | Do not dilute. |
| Roller: | Do not dilute. |
| Air-atomised spray: | Not possible. |
| Airless spray: | Not recommended. |
| Spatula: | Do not dilute. |
| Thinning: | If preferred 3486 can be diluted with Rust-Oleum Thinner 7301. |
| Cleanup: | Direct with white spirit. |

APPLICATION CONDITIONS

Can be applied during all weather conditions, except for snow. (-10°C to +35°C).

REMARKS

- Product can be recoated with Mathys Dakfill New, Coating PRT or Dac Alu.
- Never apply the product on polystyrene insulation or onto new concrete. Not suitable for use in swimming pools, ponds or baths.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk