

# TECHNICAL DETAILS

## 1-2-3 MAINTENANCE PRODUCTS\*

Product	Coverage	To touch	To handle	To recoat	Full hardness	Heat resistance	Page
<b>HARD HAT® Industrial aerosols</b>							
Paint stripper 2910 / Green paint stripper 2950	2-3 m <sup>2</sup> /can	-	-	-	-	-	6
Anti-rust primers 2169/2182	3-4 m <sup>2</sup> /can	15 min	30 min	<1 hr or >48 hrs	7 days	100°C	7
Adhesion primer 2102	5-6 m <sup>2</sup> /can	-	-	>30 min <24 hrs	-	100°C	7
Galva Zinc 2185	2-3 m <sup>2</sup> /can	10 min	30 min	<1 hr or >48 hrs	7 days	450°C	9
Galva Zinc 1085	10.5 m <sup>2</sup> /can	12 min	2 hrs	4 hrs	7 days	100°C	9
Galva Expresse 2180	2-3 m <sup>2</sup> /can	5 min	10 min	<1 hr or >48 hrs	3 days	350°C	9
Galva Zinc-Alu 2117	2-3 m <sup>2</sup> /can	20 min	60 min	<2 hrs or >48 hrs	7 days	450°C	9
Galva Zinc-Alu 1017	10 m <sup>2</sup> /can	30 min	3 hrs	-	7 days	100°C	9
Galva Plus 2120	2-3 m <sup>2</sup> /can	15 min	60 min	<2 hrs or >48 hrs	7 days	150°C	9
RAL topcoats 2100	3-4 m <sup>2</sup> /can	15 min	30 min	<1 hr or >48 hrs	7 days	100°C	10
Metallic topcoats 2111/2115	3-4 m <sup>2</sup> /can	15 min	30 min	<1 hr or >48 hrs	3 days	100°C	12
Stainless steel coating 2116	3-4 m <sup>2</sup> /can	15 min	30 min	<1 hr or >48 hrs	3 days	100°C	14
Fluorescent topcoats 2200	3-4 m <sup>2</sup> /can	15 min	30 min	<1 hr or >48 hrs	3 days	100°C	15
Clear topcoat 2500	3-4 m <sup>2</sup> /can	15 min	30 min	<1 hr or >48 hrs	3 days	100°C	15
Marking paint 2300	70 m/can	20 min	4 hrs	<1 hr or >48 hrs	3 days	100°C	18
Striping paint 2300	120 m/can	20 min	4 hrs	<1 hr or >48 hrs	3 days	100°C	18
Heat-resistant 7715/7778	3-4 m <sup>2</sup> /can	1 hr	3 hrs	<1 hr or >48 hrs	24 hrs	750°C	16
Anti-slip spray 2400	3-4 m <sup>2</sup> /can	20 min	60 min	60 min	3 days	100°C	17
Stain blocker 2990	3-4 m <sup>2</sup> /can	5 min	-	30 min	24 hrs	-	17
<b>CombiColor® metal protection</b>							
CombiColor® RAL (brush)	10.5 m <sup>2</sup> /l	2 hrs	8 hrs	16 hrs	7 days	90°C	20
CombiColor® RAL (aerosol)	2-3 m <sup>2</sup> /can	1 hr	6 hrs	2 hrs	7 days	90°C	20-23
CombiColor® Hammertone (brush)	10.5 m <sup>2</sup> /l	1,5 hrs	5 hrs	16 hrs	7 days	90°C	20-23
CombiColor® Hammertone (aerosol)	2-3 m <sup>2</sup> /can	1 hrs	4 hrs	2 hrs	7 days	90°C	20-23
CombiColor® Wrought iron (brush)	10.5 m <sup>2</sup> /l	2 hrs	8 hrs	16 hrs	7 days	90°C	20-23
CombiColor® Wrought iron (aerosol)	2-3 m <sup>2</sup> /can	1 hr	2 hrs	2 hrs	7 days	90°C	20-23
CombiPrimer® 3369/3380 (brush)	12 m <sup>2</sup> /l	1 hr	2 hrs	2 hrs	7 days	120°C	20-23
CombiPrimer® 3369/3380 (aerosol)	2-3 m <sup>2</sup> /can	15 min	30 min	<1 hr or >48 hrs	7 days	100°C	23
CombiPrimer® 3302 (brush)	35 m <sup>2</sup> /l	-	-	>30 min <24 hrs	-	100°C	23
CombiPrimer® 3302 (aerosol)	4-5 m <sup>2</sup> /can	-	-	>30 min <24 hrs	-	100°C	23
<b>Shoppers</b>							
Shopper 6400	12 m <sup>2</sup> /l	1 hr	2 hrs	24 hrs	7 days	120°C	25
Shopper 6400 WB	11.5m <sup>2</sup> /l	30 min	1 hr	1 hr	3 days	-	25
<b>7100 Floor coating</b>							
7100 Floor coating	8 m <sup>2</sup> /l	6 hrs	24 hrs	24 hrs	7 days	-	34-35
7100NS Anti-slip coating	8 m <sup>2</sup> /l	6 hrs	24 hrs	24 hrs	7 days	-	35
<b>Waterproofing</b>							
Waterproofing	1 - 2,5 m <sup>2</sup>	4 hrs	-	3 - 14 days		40°C	40
<b>EpoxyShield®</b>							
Sealer 5220 Gloss	10 m <sup>2</sup> /l	1 hr	6 hrs	6 hrs	12 hrs	-	28
Ultra 5200 Silk Matt	9 m <sup>2</sup> /l	2 hrs	6 hrs	6 hrs	7 days	-	28
Maxx 5300 Gloss	7 m <sup>2</sup> /l	16 hrs	2 days	2 days	7 days	-	29
2901.5 Cleaner/degreaser	6-8 m <sup>2</sup> /l	-	-	-	-	-	32
<b>Repair products</b>							
Concrete repair Mortar	0,4 m <sup>2</sup> / 10Kg	-	-	2 days	1 month	-	32
Fine Crack Repair	25 m linear	3 to 4 hrs	4 hrs	4 hrs	-	-	33

\*For complete product information, we refer to the respective product- and safety datasheets. ([www.123maintenance.com](http://www.123maintenance.com))

